


AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions, and listings, of claims in the application.

Listing of Claims:

1. **(Currently Amended)** A silicone adhesive exhibiting pressure-sensitive adhesion and permanent adhesion, comprising

(A) 100 parts by weight of an organopolysiloxane partial condensate obtained by partial condensation of (i) a diorganopolysiloxane having a hydroxyl radical at an end of its molecular chain, represented by the following general formula (1):



wherein R^1 and R^2 each are a substituted or unsubstituted monovalent hydrocarbon radical, and m is an integer of 500 to 10,000, with (ii) an organopolysiloxane copolymer having hydroxyl radicals in a molecule and consisting essentially of $\text{R}^3_3\text{SiO}_{1/2}$ units and $\text{SiO}_{4/2}$ units in a molar ratio of $\text{R}^3_3\text{SiO}_{1/2}$ units to $\text{SiO}_{4/2}$ units of from 0.5 to 1.5, wherein R^3 is a hydroxyl radical or a substituted or unsubstituted monovalent hydrocarbon radical,

(B) 0.1 to 20 parts by weight of a silane or siloxane compound having a silicon atom-bonded alkoxy radical and an organic radical or atom selected from the group consisting of an alkenyl radical, an epoxy radical and a silicon atom-bonded hydrogen atom, a silane or siloxane compound having an epoxy radical and a silicon atom-bonded hydrogen atom, or a mixture thereof, and

(C) a crosslinking agent.

2. **(Previously Presented)** The silicone adhesive of claim 1 wherein the crosslinking agent (C) is an organic peroxide.


3. **(Previously Presented)** The silicone adhesive of claim 1 wherein the crosslinking agent (C) comprises (a) an organohydrogenpolysiloxane having at least two silicon atom-bonded hydrogen atoms in a molecule, in an amount to give 0.2 to 30 mol of silicon atom-bonded hydrogen atoms per mol of alkenyl radicals in components (A) and (B), and (b) a catalytic amount of a platinum base catalyst.

4. **(Previously Presented)** A silicone adhesive film prepared by forming the adhesive of claim 1 into a film shape.

5. **(Previously Presented)** A silicone rubber adhesive film prepared by forming the adhesive of claim 1 into a film shape, followed by crosslinking and curing.

6. **(New)** A silicone adhesive exhibiting pressure-sensitive adhesion and permanent adhesion, said silicon adhesive comprising:

(A) 100 parts by weight of an organopolysiloxane partial condensate obtained by partial condensation of (i) a diorganopolysiloxane having a hydroxyl radical at an end of its molecular chain, represented by the following general formula (1):



wherein R¹ and R² each are a substituted or unsubstituted monovalent hydrocarbon radical, and m is an integer of 500 to 10,000, with (ii) an organopolysiloxane copolymer having hydroxyl radicals in a molecule and consisting essentially of R³₃SiO_{1/2} units and SiO_{4/2} units in a molar ratio of R³₃SiO_{1/2} units to SiO_{4/2} units of from 0.5 to 1.5, wherein R³ is a hydroxyl radical or a substituted or unsubstituted monovalent hydrocarbon radical,

(B) 0.1 to 20 parts by weight of a silane or siloxane compound having a silicon atom-bonded alkoxy radical and an alkenyl group or an epoxy radical, a silane or siloxane compound having an epoxy radical and a silicon atom-bonded hydrogen atom, or a mixture thereof, and

(C) (a) an organohydrogenpolysiloxane having at least two silicon atom-bonded hydrogen atoms in a molecule, in an amount to give 0.2 to 30 mol of silicon atom-bonded hydrogen atoms per mol of alkenyl radicals in components (A) and (B), and (b) a catalytic amount of a platinum base catalyst.

7. (New) A silicone adhesive film prepared by forming the adhesive of claim 6 into a film shape.

8. (New) A silicone rubber adhesive film prepared by forming the adhesive of claim 6 into a film shape, followed by crosslinking and curing.